



33

IGP Powder Coatings

TDS IGP-DURA®mix 3305A-C0|240424|v2.3

This application-related advice is given to the best of our knowledge. However, this information is non-obligatory and does not exempt you from carrying out your own tests. Application, use and processing of these products are beyond our control and are therefore on your responsibility.

Consult the Safety Data Sheet prior to use. Article-specific safety data sheet and comprehensive risk management measures available at: **igp-powder.com**

IGP Powder Coatings

TDS IGP-DURA®mix 3305A-C0|240424|v2.3

Technical data sheet

## IGP-DURA®mix 3305A-C0

Silk matte, elegant powder coating with electrostatically discharging properties (ESD).



### Characteristics

- Silk matte
- Smooth finish
- Uni colors
- Indoor quality
- Electric. discharging



### Powder properties

Particle size:

Solids:

Density:

Suitability for storage:

< 3.94 mil  
> 99 %  
10.85 lb/gal-13.35 lb/gal  
min. 24 months at  $\leq 77$  °F  
in an unopened original container  
Color tones:  
On request

---



## Processing

### Pre-treatment

The substrate must be free from oil, grease and oxidation products. The pretreatment depends on the type of substrate and the corrosion protection to be achieved. We recommend the following pretreatments:

#### Aluminum

- Chromating according to DIN EN 12487
- Pre-anodization
- Chrome-free pretreatment according to GSB International and QUALICOAT specifications

#### Steel

- Zinc phosphating

#### Galvanized steel

- Zinc phosphating
- Chrome (III) passivation
- Chromating according to DIN EN 12487

The suitability of the pretreatment method used is generally to be tested by the coater in advance with appropriate test methods. The minimum requirement for aluminium substrates / galvanised steel components is to carry out a boiling water test with a subsequent cross-cut adhesion and tape test. We refer to the guidelines of the GSB International, Qualicoat and Qualisteelcoat certifications. For further information: see also our special leaflet on pre-treatment (IGP-TI 100).

#### Coating devices


All commercially available electrostatic systems, both corona and tribo charge systems. For the construction and operation of powder coating plants, the following regulations must be complied with: ATEX RL 2014/34/EU, EN 50177, DIN EN 16985.

#### Recommended film thickness

2.36 mil - 3.15 mil

With higher layers, the powder coating becomes insulating.

#### Curing conditions



T <sub>Object</sub>	t <sub>min</sub>	t <sub>max</sub>
356 °F	15 minutes	25 minutes
374 °F	10 minutes	15 minutes
392 °F	8 minutes	12 minutes

In order to determine ideal curing conditions, we recommend practical trials with the object in question and curing oven.



## Film properties

Tested on

Substrate:

Steel, 0.5 mm

Film thickness:

2.36 mil - 3.15 mil

Object temperature:

374 °F, 10 min.

Appearance

Gloss level

45-55 R'/60°

DIN EN ISO 2813 2015-02

Mechanical tests

Cross-cut adhesion test

Gt 0  
DIN EN ISO 2409 2020-12  
Mandrel bending test  
≤ 5 mm  
DIN EN ISO 1519 2011  
Impact test  
≥ 10 inchp.  
ASTM D 2794 1993  
Erichsen cupping  
≥ 5 mm  
DIN EN ISO 1520 2007-11  
Buchholz hardness  
≥ 80  
DIN EN ISO 2815 2003-10  
Corrosion tests  
Condensation water test, 500-1000h\*  
No infiltration, no blisters. \*depending on pretreatment  
DIN EN ISO 6270-2 2018-04  
Natural salt spray test, 500-1000h  
No infiltration, no blisters. \*depending on pretreatment.  
DIN EN ISO 9227 2017-07  
Chemical tests  
Acids and alkalis  
Good resistance to many dilute acids and alkalis.  
Organic solvents  
Limited resistance to organic solvents.  
Additional properties  
electrostatic discharge resistance  
TI 101  
DIN EN 61340-2-3 2017-05

---



## More information

### Packaging

20 kg cardboard box with inserted antistatic PE liner

500 kg cardboard container with 25 antistatic PE-liners each 20kg

### Protection of coated parts

Coated parts should be packed after cooling with suitable materials without plasticizers. They should be stored protected from the weather to avoid the formation of condensation and thus water spots on the coating.

### Cleaning

The coated parts must be cleaned according to the directives RAL-GZ 632 or SZFF 61.01.

### Paint removal and disposal

After use, coated goods should be supplied to the normal recycling process. The disposal methods for sludges or residual powders must be observed in accordance with the local official provisions whilst taking Waste Code “080201 Coating Powder Wastes” in accordance with the European Waste Catalogue into consideration.