



51

IGP Powder Coatings

TDS IGP-DURA®vent 511TA-A0|240424|v1.2

This application-related advice is given to the best of our knowledge. However, this information is non-obligatory and does not exempt you from carrying out your own tests. Application, use and processing of these products are beyond our control and are therefore on your responsibility.

Consult the Safety Data Sheet prior to use. Article-specific safety data sheet and comprehensive risk management measures available at: **igp-powder.com**

IGP Powder Coatings

TDS IGP-DURA®vent 511TA-A0|240424|v1.2

Technical data sheet

## IGP-DURA®vent 511TA-A0

Deep matt powder coating with a fine texture and excellent corrosion protection for use on outgassing substrates.



### Characteristics

- Deep matte
- Fine texture
- Uni colours
- Standard facade quality,  
1 year Florida > 50% residual gloss
- Degassing optimized



### Material approvals

- QSC HD1 PE-0096





## Powder properties

Particle size:

Solids:

Density:

Suitability for storage:

< 100 µm

> 99 %

1.3 kg/l-1.6 kg/l

min. 18 months at ≤ 25 °C

in an unopened original container

Color tones:

RAL and NCS-S shades, individual colors on request

---



## Processing

Pre-treatment

The substrate must be free from oil, grease and oxidation products. The pretreatment depends on the type of substrate and the corrosion protection to be achieved. We recommend the following pretreatments:

Aluminium

- Chromating according to DIN EN 12487
- Pre-anodization
- Chrome-free pretreatment according to GSB International and QUALICOAT specifications

Steel

- Zinc phosphating

Galvanised steel

- Zinc phosphating
- Chrome (III) passivation
- Chromating according to DIN EN 12487

For improved corrosion protection for applications on steel / galvanised steel, the use of corrosion protection primer IGP-KORROPRIMER 10 or IGP-KORROPRIMER 60 is recommended.

The suitability of the pretreatment method used is generally to be tested by the coater in advance

with appropriate test methods. The minimum requirement for aluminium substrates / galvanised steel components is to carry out a boiling water test with a subsequent cross-cut adhesion and tape test. We refer to the guidelines of the GSB International, Qualicoat and Qualisteelcoat certifications. For further information: see also our special leaflet on pre-treatment (IGP-TI 100).

#### Coating devices

All commercially available electrostatic systems, both corona and tribo charge systems. For the construction and operation of powder coating plants, the following regulations must be complied with: ATEX RL 2014/34/EU, EN 50177, DIN EN 16985.


#### Recommended film thickness

60 µm - 80 µm

A homogeneous coating result with textured coatings or article-and color specific differences in hiding power may require higher coating thicknesses. The corresponding processing guidelines must be observed.

For a pre-calculation of the required powder coating quantity, the necessary coating thickness must be determined for each article.

#### Curing conditions



<b>T Object</b>	<b>t min</b>	<b>t max</b>
180 °C	10 minutes	20 minutes
190 °C	8 minutes	15 minutes
200 °C	6 minutes	10 minutes

In order to determine ideal curing conditions, we recommend practical trials with the respective object and curing oven.

#### Reclaimability

Small portions of recycled powder can be added, automatically if possible, to the fresh powder. Important: Keep overspray to an absolute minimum. Processing instruction VR214 must be observed.

---



## Film properties

Tested on

Substrate:

Steel, 0.5mm

Film thickness:

60  $\mu\text{m}$  - 80  $\mu\text{m}$

Object temperature:

190 °C, 8 min.

Appearance

Gloss level

2-12 R'/60°

DIN EN ISO 2813 2015-02

Mechanical tests

Cross-cut adhesion test

Gt 0

DIN EN ISO 2409 2020-12

Mandrel bending test

$\leq 6$  mm

DIN EN ISO 1519 2011

Impact test

$\geq 20$  inchp.

ASTM D 2794 1993

Erichsen cupping

$\geq 5$  mm

DIN EN ISO 1520 2007-11

Buchholz hardness

$\geq 80$

DIN EN ISO 2815 2003-10

Weathering

1 year Florida, 5° south

> 50 % residual gloss

DIN EN ISO 2810 2021-01

Xenon-arc lamps, 1000h

> 50 % residual gloss

DIN EN ISO 16474-2 2014-03

Corrosion tests

Natural salt spray test, 720h on HDG steel, chemical pretreatment

No infiltration, no blisters.

DIN EN ISO 9227 2017-07

Condensation water test, 480h on HDG steel, chemical pretreatment

No infiltration, no blisters.

DIN EN ISO 6270-2 2018-04

Chemical tests

Mortar resistance

Easily removable after 24h with no residues.

ASTM D 3260 2001



## **Further information**

### Packaging

20 kg cardboard box with inserted antistatic PE liner

### Overcoating

Preliminary tests are mandatory for overcoating painted surfaces.

### Printing and glueing

Preliminary tests are mandatory for printing and glueing of painted surfaces.

### Protection of coated parts

Coated parts should be packed after cooling with suitable materials without plasticizers. They should be stored protected from the weather to avoid the formation of condensation and thus water spots on the coating.

### Cleaning

The coated parts must be cleaned according to the directives RAL-GZ 632 or SZFF 61.01.

### Paint removal and disposal

After use, coated goods should be supplied to the normal recycling process. The disposal methods for sludges or residual powders must be observed in accordance with the local official provisions whilst taking Waste Code "080201 Coating Powder Wastes" in accordance with the European Waste Catalogue into consideration.